

Return address: P.O. Box 2220, 6802 CE ARNHEM, The Netherlands

Unifloor Underlay Systems  
Att. Mr. F. Vousten  
Arnsbergstraat 4  
7418 EZ DEVENTER  
The Netherlands

TÜV Rheinland Nederland B.V.  
The Netherlands

Postal address:  
P.O. Box 2220  
6802 CE ARNHEM

Parking and delivery:  
Westervoortsedijk 73  
6827 AV ARNHEM

[www.tuv.com/nl](http://www.tuv.com/nl)

T +31 88 888 7888

[Jaring.de.Wolff@nl.tuv.com](mailto:Jaring.de.Wolff@nl.tuv.com)

## Testreport

**Project number:** 89210247  
**Report number:** 89210247.10br

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Phone number client**  
+31 (0) 570 85 55 33

**Fax number client**  
+31 (0) 570 85 55 44

### **Received:**

A floor covering combination (underlay system, glue and floorcovering), marked as:  
**“Redupanel Parket, Redupanel with 4 mm CocoFloor”**;  
TÜV-reference: MT16-117021.25

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

### **Sampling procedure:**

The samples are selected by the applicant. The test house has had no influence on the sampling procedure.

The samples have been received on 15/12/2016.

### **Order:**

Classification of burning behaviour according to EN 13501-1:2007+ A1:2009.

**Appendix**  
I : Flooring Radiant Panel Single  
Specimen Report – 6 pages

Test methods: Ignitability of products subjected to direct impingement of flame (ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

### **Results:**

See page three and four.

### **Appendix:**

See page five up to and including ten.

TRN applies General Terms & Conditions which are filed at the office of the Clerk for civil affairs at the Court in Zutphen (the Netherlands) under number 35/2010, dated November 17th 2010.

## PRODUCT IDENTIFICATION

Applicant : Unifloor Underlay Systems  
Name : Redupanel Parket, Redupanel with 4 mm  
CocoFloor \*  
Production direction : No production direction applicable\*  
Total thickness (mm) : 29,8\*\*  
Total mass (gr/m<sup>2</sup>) : 14770\*\*  
Density (kg/m<sup>3</sup>) : 496\*\*

\* Applicant's declaration

\*\* Determination by the test house after conditioning to constant mass is achieved.

Date  
03/02/2017

Project number  
89210247

Report number  
89210247.10br

Article  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

Page  
2/10



Figure 1. Picture of the received sample

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
3/10

## TEST RESULTS

### *Ignitability of products subjected to direct impingement of flame* Method EN ISO 11925-2 :2010/C1:2011

Date of testing : 03/01/2017  
 Conditioning time, climate :  $\geq 7$  days,  $23 \pm 2$  °C and  $50 \pm 5$  %  
 Description of substrate : Fibre cement board,  $8 \pm 2$  mm,  $1800 \pm 200$  kg/m<sup>3</sup>  
 conforming to EN 13238.  
 Flame application : Surface.  
 Flame application time : 15 seconds.

Orientation:	Length		
Total burning time <sup>1</sup>	15	15	15
Flame tip reaches 150 mm (s)	No	No	No
Extent of damaged area, length (mm)	35	35	35
Extent of damaged area, width (mm)	12	12	10
Material melts (yes/no)	Yes	Yes	Yes
Shrinks away <sup>2</sup> (yes/no)	No	No	No
Glowing <sup>3</sup> (sec)	No	No	No
Flaming debris (yes/no)	No	No	No
Ignition of filter paper (yes/no)	No	No	No

1 Inclusive a flame application time of 15 or 30 seconds with surface or edge impingement

2 Shrinks away from flame without being ignited

3 The time at which it occurs and its duration

### *Determination of the burning behaviour using a radiant heat source* Method EN ISO 9239-1:2010

Date of testing : 11/01/2017  
 Conditioning time, climate :  $\geq 7$  days,  $23 \pm 2$  °C and  $50 \pm 5$  %  
 Description of substrate : Fibre cement board,  $8 \pm 2$  mm,  $1800 \pm 200$  kg/m<sup>3</sup>  
 conforming to EN 13238.  
 Sampling procedure : By contractor.  
 Description of cleaning used : None.  
 Fixing method : None, sample is tested loose laid on the substrate.

Test specimen	Flame spread (cm)	CRF (kW/m <sup>2</sup> )	Peak light attenuation (%)	Smoke production (%.min)
1	35.0	6.6	2.0	13
2	32.0	7.3	1.8	12
3	35.0	6.6	2.0	13
<b>Mean</b>	<b>34.0</b>	<b>6.8</b>	<b>1.9</b>	<b>13</b>

Note: according the manufacturers declaration there is no production direction applicable, therefore three samples are sufficient for classification.

Specimen 1, 2, and 3: No flashing, transitory- or sustained flaming are observed.

Specimen 1: Extinguished manually after the end of the test duration

Specimen 2 and 3: Extinguished naturally before the end of the test duration

Date  
03/02/2017

Project number  
89210247

Report number  
89210247.10br

Article  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

Page  
4/10

## CONCLUSION

According to EN 13501-1:2007+ A1:2009 the tested sample of the aforementioned quality “Redupanel Parket, Redupanel with 4 mm CocoFloor”, in relation to its reaction to fire behaviour is classified: C<sub>n</sub>.

The additional classification in relation to smoke production is: s1.

The aforementioned quality meets the requirement of reaction to fire classification:  
C<sub>n</sub> – s1

The classification is valid for the following end use applications:

- End use substrates of classes A1 and A2-s1,d0.
- Any way of fixation, glued down or loose laid.

### Statements:

The test results only relate to the behaviour of the test specimens of the examined product under the particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. The method might not be suitable if the product is exposed to much larger flames or heat radiant sources.

The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria. This report shall not be reproduced, except in full, without the written approval of the testing laboratory.

This document does not represent type approval or certification of the product.

Author:  
Mr. M.A. van de Vlekkert



Review:  
Mr. J. de Wolff



*All rights reserved.*

*No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V. The results are based upon the samples received and have not to be representative for the total production. TÜV Rheinland Nederland B.V. had no influence on the sampling.*

*In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties.*

© 2010 TÜV Rheinland Nederland B.V.

(End of report)

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
5/10

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 1

### Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010  
Laboratory : TÜV Rheinland Nederland B.V.  
Sponsor : 89210247 Unifloor  
Date of test : Jan. 11 2017

Specimen description : MF16-117021.25 Redupanel Parket / Redupanel  
Test name : # sample 1  
File name : D:\FRPFILES\17010036.CSV  
Test number in series : 3

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX16016.CSV

Thickness (mm) : 29.8  
Density (kg/m<sup>3</sup>) : 496

Test duration : 30 minutes (1800 s)  
Substrate used? : Yes  
Substrate : Calcium silicate  
Fixing method : None (loose laid)  
Conditioned? : Yes  
Conditioning temp. (°C) : 23  
Conditioning RH (%) : 50

#### Test Results

Time to ignition : 2 minutes 03 seconds (123 s)  
Time to flameout : 30 minutes (1800 s)  
Extent of burning (mm) : 350  
Critical flux at extinguishment (kW/m<sup>2</sup>) : 6.59  
HF-10 (kW/m<sup>2</sup>) : 10.00  
HF-20 (kW/m<sup>2</sup>) : 7.49  
HF-30 (kW/m<sup>2</sup>) : 6.59  
Flame spread at 10 minutes (mm) : 160  
Flame spread at 20 minutes (mm) : 310  
Flame spread at 30 minutes (mm) : 350  
Peak light attenuation (%) : 2.01  
Time to peak light attenuation : 29 minutes 17 seconds (1757 s)  
Total integrated smoke (%.min) : 13.44

**Potential classification** : C(f)  
**Smoke production classification** : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSafe software


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parquet, Redupanel  
with 4 mm CocoFloor

**Page**  
6/10



Test name : # sample 1  
File name : D:\FRPFILES\17010036.CSV

### Rake Results

Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )	Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )
60	315	11.1	3.489	510	-	3.7	-
110	535	10.5	5.608	560	-	3.1	-
160	608	10.0	6.080	610	-	2.6	-
210	822	9.4	7.225	660	-	2.2	-
260	1039	8.4	8.739	710	-	1.9	-
310	1211	7.5	9.064	760	-	1.6	-
360	-	6.4	-	810	-	1.4	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.1	-

### Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

Page 1

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
7/10

### Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010  
Laboratory : TÜV Rheinland Nederland B.V.  
Sponsor : 89210247 Unifloor  
Date of test : Jan 11 2017

Specimen description : MT16-117021.15 Redupanel Parket / Redupanel  
Test name : # sample 2  
File name : D:\FRPFILES\17010037.CSV  
Test number in series : 3

Flux calibration file name : C:\FRPSOFT\2.9A\CALIB\FIX16016.CSV

Thickness (mm) : 29.8  
Density (kg/m<sup>3</sup>) : 496

Test duration : 26 minutes 19 seconds (1579 s)  
Substrate used? : Yes  
Substrate : Calcium silicate  
Fixing method : None (loose laid)  
Conditioned? : Yes  
Conditioning temp. (°C) : 23  
Conditioning RH (%) : 50

#### Test Results

Time to ignition : 2 minutes 03 seconds (123 s)  
Time to flameout : 26 minutes 17 seconds (1577 s)  
Extent of burning (mm) : 320  
Critical flux at extinguishment (kW/m<sup>2</sup>) : 7.26  
HF-10 (kW/m<sup>2</sup>) : 10.10  
HF-20 (kW/m<sup>2</sup>) : 7.67  
HF-30 (kW/m<sup>2</sup>) : Not calculated (test duration < 30 minutes)  
Flame spread at 10 minutes (mm) : 150  
Flame spread at 20 minutes (mm) : 300  
Flame spread at 30 minutes (mm) : Not measured  
Peak light attenuation (%) : 1.81  
Time to peak light attenuation : 22 minutes 29 seconds (1349 s)  
Total integrated smoke (%.min) : 11.92

**Potential classification** : C(II)  
**Smoke production classification** : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 2


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
8/10



Test name : # sample 2  
File name : D:\FRPFILES\17010037.CSV

### Rake Results

Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )	Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )
60	293	11.1	3.245	510	-	3.7	-
110	519	10.5	5.441	560	-	3.1	-
160	646	10.0	6.460	610	-	2.6	-
210	831	9.4	7.810	660	-	2.2	-
260	1039	8.4	8.739	710	-	1.9	-
310	1311	7.5	9.813	760	-	1.6	-
360	-	6.4	-	810	-	1.4	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.1	-

### Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology FRPSoft software

page 1

**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
9/10

### Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010  
 Laboratory : TÜV Rheinland Nederland B.V.  
 Sponsor : 89210247 Unifloor  
 Date of test : Jan. 11 2017

Specimen description : MT16-117021.25 Redupanel Parket / Redupanel  
 Test name : # sample 3  
 File name : D:\FRPFILES\17010038.CSV  
 Test number in series : 3

Flux calibration file name : C:\FRPSOFT\2.9A\CALIB\FLX16016.CSV

Thickness (mm) : 29.8  
 Density (kg/m<sup>3</sup>) : 496

Test duration : 26 minutes 45 seconds (1605 s)  
 Substrate used? : Yes  
 Substrate : Calcium silicate  
 Fixing method : None (loose laid)  
 Conditioned? : Yes  
 Conditioning temp. (°C) : 23  
 Conditioning RH (%) : 50

#### Test Results

Time to ignition : 2 minutes 07 seconds (127 s)  
 Time to flameout : 26 minutes 43 seconds (1603 s)  
 Extent of burning (mm) : 350  
 Critical flux at extinguishment (kW/m<sup>2</sup>) : 6.59  
 HF-10 (kW/m<sup>2</sup>) : 10.00  
 HF-20 (kW/m<sup>2</sup>) : 7.49  
 HF-30 (kW/m<sup>2</sup>) : Not calculated (test duration < 30 minutes)  
 Flame spread at 10 minutes (mm) : 160  
 Flame spread at 20 minutes (mm) : 310  
 Flame spread at 30 minutes (mm) : Not measured  
 Peak light attenuation (%) : 2  
 Time to peak light attenuation : 26 minutes 45 seconds (1605 s)  
 Total integrated smoke (%.min) : 15.37

**Potential classification** : C(II)  
**Smoke production classification** : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

## APPENDIX I: Flooring Radiant Panel Single Specimen Report

Report produced with the Fire Testing Technology's FRPSoft software

page 2


**Date**  
03/02/2017

**Project number**  
89210247

**Report number**  
89210247.10br

**Article**  
Redupanel Parket, Redupanel  
with 4 mm CocoFloor

**Page**  
10/10



Test name : # sample 3  
File name : D:\FRPFILES\17010038.CSV

### Rake Results

Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )	Position (mm)	Time (s)	Flux (kW/m <sup>2</sup> )	Qsb (MJ/m <sup>2</sup> )
60	358	11.1	3.965	510	-	3.7	-
110	469	10.5	4.917	560	-	3.3	-
160	627	10.0	6.270	610	-	2.6	-
210	803	9.4	7.547	660	-	2.2	-
260	955	8.4	8.033	710	-	1.9	-
310	1193	7.5	8.930	760	-	1.6	-
360	-	6.4	-	810	-	1.4	-
410	-	5.3	-	860	-	1.2	-
460	-	4.4	-	910	-	1.1	-

### Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.